

## Typical Magnetic Performance for Cast FeCrCo

Grade	Br		Hcb		Hcj		BHmax		Density	Remark
	kGs	mT	kA/m	Oe	kA/m	Oe	KJ/m3	MGOe	g/cm3	
FeCrCo10/3	8.20	820	27	340	29	360	10	1.25	7.6	Isotropic
FeCrCo12/4	8.00	800	40	500	42	530	12	1.50	7.6	
FeCrCo28/5	10.00	1000	45	570	46	580	28	3.50	7.6	Anisotropic
FeCrCo30/4	11.50	1150	40	500	41	510	30	3.80	7.6	
FeCrCo35/5	10.50	1050	50	630	51	640	35	4.40	7.6	
FeCrCo36/5	12.00	1200	52	660	54	680	36	4.50	7.8	
FeCrCo44/4	13.00	1300	44	560	45	570	44	5.50	7.7	
FeCrCo52/5	13.50	1350	48	600	49	620	52	6.50	7.7	